



4076



**SIEVE ANALYSIS**

Client: Nick Brookes  
 Site: Wardle Depot  
 Location: Stockpile  
 Date Sampled: 20/10/11  
 Sampled from: Stockpile  
 Supplier: Client  
 Description: 6F5 Capping


Report No. 1119-N-04-A-26

Laboratory Ref: Lab/11/3988  
 Client Ref. Tr1/20/10  
 Mass (kg): 46  
 Source: Site

Material Specification: 6F5 to SHW Table 6/5  
 Sampled by: Client  
 Date received: 24/10/11  
 Sample type: Bulk  
 Method of Preparation:

Remarks: Sample complies with grading specification  
 Moisture Content = 6

BS Sieve (mm)	Passing (%)	Material Specification		
125	100	100	-	-
80	97	75	-	99
75	81			
63	76			
40	71	50	-	90
31.5	69			
20	60	30	-	75
16	56			
14	53			
10	47	15	-	60
8.0	42			
6.3	37			
4.0	31			
2.0	26	0	-	35
1.0	22			
0.500	19			
0.250	14			
0.125	10			
0.063	8.4	0	-	12



Certified that the Particle Size Distribution was determined in accordance with EN 933-1

Signed \_\_\_\_\_ ( ) M. Hayes (Laboratory Manager)  
 ( ) D.Foster (Assistant Laboratory Manager)  
 ( X ) J.Hopkinson (Senior Technician)